

Interline 925

Solvent free potable water lining

When it comes to potable water linings, Interline[®] 925 is hard to beat. It can be applied as a single coat using standard application equipment.

- Solvent free, high build, amine cured epoxy tank lining
- Certified to NSF/ANSI 61, BS6920, AS/NZS 4020 standards for the storage of potable water
- Hard, glossy coating which provides a long-life, easy clean, low maintenance surface for safe, taint-free potable water storage
- Provides additional resistance to a range of cargoes including potable water, crude oil and a variety of other hydrocarbons
- 100% solids, zero VOC formulation which eliminates solvent emission, explosion risk and fire hazard
- Suitable for application as a single coat system, using standard airless spray equipment



Solvent free, high build, amine cured epoxy tank lining

Interline® 925 is a two component, solvent free, heavy duty epoxy lining. It provides corrosion protection for the internals of pipelines and steel storage tanks exposed to a wide range of cargoes including potable water, crude oil and a variety of other hydrocarbons.

When applied to the correct specifications, Interline® 925 conforms to the following international standards for the storage of potable water:

- NSF/ANSI Standard 61
- BS6920
- AS/NZ 4020



With a 100% volume solids, zero VOC formulation, Interline® 925 is designed to reduce solvent emissions and eliminate the risk of solvent retention, which can influence water quality.

Suitable for application as a single coat system using standard airless spray equipment. This assists with contract schedules.

Interline® 925 may be used as a topcoat for reinforced linings to provide additional corrosion protection to deteriorated surfaces.



Test data

TEST TYPE	REFERENCE	DETAILS	RESULTS
Pull-off adhesion	ISO 4624	1 x 400µm (16 mils) dft Interline® 925 applied directly to Sa2.5 (SSPC-SP10) blasted steel	Not less than 12Mpa (1740psi) when using PAT Model GM01 hydraulic adhesion tester on 5mm thick steel
Impact resistance	ASTM D2794	1 x 400µm (16 mils) dft Interline® 925 applied directly to Sa2.5 (SSPC-SP10) blasted steel	Direct impact resistance typically 2.2 Joules
Abrasion resistance	ASTM D4060	1 x 400µm (16 mils) dft Interline® 925 applied directly to Sa2.5 (SSPC-SP10) blasted steel	Average of 65mg weight loss per 1,000 cycles using CS10 wheels and a 1Kg loading
Immersion	ISO 2812 Part 2	1 x 400µm (16 mils) dft Interline® 925 applied directly to Sa2.5 (SSPC-SP10) blasted steel	No film defects following 8,000 hours exposure
Elongation at break	ASTM D2370	1 x 400µm (16 mils) dft "free film"	An average of 1.6% elongation of the coating is achieved prior to fracture
Tensile strength	ASTM D2370	1 x 400µm (16 mils) dft "free film"	An average of 15MPa (2,176psi) is required to achieve fracture of the coating

The above performance data has been compiled based on present experience of in-service product performance and upon performance data obtained under laboratory test conditions. Actual performance of the product will depend upon the conditions in which the product is used.

www.international-pc.com
pc.communication@akzonobel.com

All trademarks mentioned in this publication are owned by the AkzoNobel group of companies. © Akzo Nobel 2014. AkzoNobel has used its best endeavors to ensure that the information contained in this publication is correct at the time of printing. Please contact your local representative if you have any questions.

Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale.